

**TE67**
**TEMACOAT HB PRIMER  
TEMACOAT HB 30**

The epoxy systems TE67 are recommended for steel, stainless steel, aluminium and zinc surfaces exposed to abrasion, chemicals, high humidity and climate in indoor and outdoor applications.

<b>Corrosivity categories/durability according to ISO 12944/ SFS 5873</b>	<b>Tikkurila Coatings code</b>	<b>Treatment</b>
<b>Steel surfaces</b>		
<b>S1.28, S2.16, S3.17</b> <b>Corrosivity categories/durability C2-H, C3-M</b> Steelwork exposed to moderate climatic conditions. According to SFS 5873, system S3.17	<b>TE67</b> TEMACOAT HB PRIMER TEMACOAT HB 30	<b>EP160/2-FeSa2½</b> 80 µm <u>80 µm</u> DFT 160 µm
<b>S1.34, S3.19, S4.13</b> <b>Corrosivity categories/durability C3-H, C4-M</b> Steelwork and equipment in severe environment, exposed to splashes and dust.	<b>TE67</b> TEMACOAT HB PRIMER TEMACOAT HB 30	<b>EP240/3-FeSa2½</b> 2 x 80 µm <u>80 µm</u> DFT 240 µm
<b>S5.14</b> <b>Corrosivity categories/durability C5-I-H, C5-M-M</b> Steel constructions and equipment exposed to very severe gas and chemical dust attacks. Paint system according to SFS 5873.	<b>TE67</b> TEMACOAT HB PRIMER TEMACOAT HB 30	<b>EP300/2-FeSa2½</b> 150 µm <u>150 µm</u> DFT 300 µm

**Marking of paint systems: TE67-SFS EN ISO 12944-5/S3.17 (EP160/2-FeSa2½)**

**Aluminium surfaces**

<b>Corrosivity categories C2, C3, C4</b> Aluminium surfaces exposed to abrasion and moderate gas and chemical dust attack. According to SFS 5873, system F40.05	<b>TE67</b> TEMACOAT HB PRIMER TEMACOAT HB 30	<b>EP120/2-AISaS</b> 60 µm <u>60 µm</u> DFT 120 µm
---	---	--

**Zinc surfaces (hot-dip galvanized)**

<b>S9.10</b> <b>Corrosivity categories/durability C3-H, C4-M, C5-L</b> Zinc surfaces, indoors exposed to abrasion and moderate gas and chemical dust attack. According to SFS 5873, system F40.05	<b>TE67</b> TEMACOAT HB PRIMER TEMACOAT HB 30	<b>EP120/2-ZnSaS</b> 60 µm <u>60 µm</u> DFT 120 µm
<b>S9.11</b> <b>Corrosivity categories/durability C4-H, C5-I-L, C5-M-M</b> Zinc surfaces, indoors exposed to mechanical abrasion and moderate gas and chemical dust attack.	<b>TE67</b> TEMACOAT HB PRIMER TEMACOAT HB 30	<b>EP160/2-ZnSaS</b> 80 µm <u>80 µm</u> DFT 160 µm

**COLOURS**

The product is tintable with TEMASPEED colorants, thus ensuring the possibility to get shades from RAL-, BS-, NCS- and other colour cards.

**SUITABLE SHOP PRIMERS**

TEMABLAST EV 110, epoxy shop primer.  
SD ZINC 1000 HA, zinc silicate

---

**SURFACE PREPARATION**

Remove firm contaminations in order to make the cleaning easier. Remove salts, grease and oil with a suitable detergent. Rinse the surfaces thoroughly with water. ( ISO 12944 )

**Steel surfaces:**

Blast clean steel surfaces to preparation grade Sa2½. ( ISO 8501 - 1 )

**Zinc surfaces:**

Sweep blast-clean with mineral abrasives, e.g. quartz sand, to grade SaS. (SFS 5873). If blast cleaning isn't possible, the surfaces should be roughened by grinding or washed with PANSSARIPESU detergent. In these cases the adhesion of the paint to the substrate should be confirmed.

Damages in the zinc coating have to be repaired with TEMAZINC 99, a zinc rich epoxy paint. Before painting, clean the surfaces thoroughly (Sa2½/St3) and level off the edges around the cleaned areas.

**Aluminium surfaces:**

Sweep blast-clean with none-metallic abrasives to grade SaS. (SFS 5873). If blast cleaning isn't possible, the surfaces should be roughened by grinding or washed with MAALIPESU detergent. In these cases the adhesion of the paint to the substrate should be confirmed.

**APPLICATION CONDITIONS**

The surface must clean and dry and the surface temperature should remain at least 3 °C/ 5 °F above the dew point. During application and drying the temperature of the air, paint and surface should be a minimum of + 10 °C/50 °F. The relative humidity should not exceed 80 %.

**APPLICATION**

The paint should be mixed thoroughly before application and then applied in an even coat on the dry and clean surface. Application with airless or conventional spray, brush or roller. Stripe coating of sharp edges, welding seams etc. should be done by brush or roller.

**MAINTENANCE PAINTING****Maintenance**

Touch-up painting is sufficient for maintenance when the rust grade is Ri1 - Ri3. ( ISO 4628-3 )

Damages caused by transport or installation may also be repaired by touch-up painting. Remove all loose paint, clean rusty areas according to system demands. On steel surfaces small areas can be grinded or wire brushed to preparation grade St2 (SFS-ISO 8501-1).

Level off the edges between the old paint film and the cleaned up areas. When using blast cleaning, be sure that there are no cracks in the remaining paint film. If the entire surface has to be overcoated, abrade the old topcoat to a rough finish. Remove all dust and other cleaning residues. Apply primers and finish according to the original paint system, qualities and film thicknesses.

**Repainting**

When the rust grade is Ri4 or Ri5, the entire coating must be renewed. Remove the old paint film and clean the surfaces to preparation grade Sa 2½. Recoat in accordance with the original paint system.

**PRODUCT INFORMATION**

More detailed product information is available in respective data sheets.