

TEMALUX 70

DESCRIPTION

A two component glossy high build oxirane ester paint.

PRODUCT FEATURES AND RECOMMENDED USES

 Suitable for both industrial finishing and heavy-duty anticorrosion coating for steel surfaces.

- Can be used as a single coat, as a primer and a topcoat.
- ♦ Environmentally more friendly and for users a more safe alternative than epoxy and polyurethane paints. High volume solids and does not contain any amines or isocyanates.
- Can be cured at higher temperatures.
- Not suitable for immersion.

TECHNICAL DATA

Volume solids $65 \pm 2 \%$. (ISO 3233)

Weight solids $78 \pm 2 \%$.

Specific gravity 1.3 - 1.5 kg / I (mixed) depending on colour.

Mixing ratio and
product codesBase
Hardener2 parts
1 part

2 parts by volume 519-series 1 part by volume 008 7670

Pot life 4 hours (23 °C / 74 °F)

Recommended film thicknesses and theoretical coverage

Recommended film thicknesses		Theoretical coverage	
dry	wet		
60 µm	95 μm	10.8 m ² /l	
100 μm	155 μm	6.5 m ² /l	
Recommended film thicknesses/"wet-on-wet"	dry	wet	
	80 μm	125 μm	
	160 μm	250 μm	

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying time

DFT 80 µm	+ 10 °C	+ 23 °C	+ 35 °C
Dust dry	3 h	1 - 1½ h	1 h
Touch dry	10 h	4 - 5 h	3 h
Recoatable	10 h	4 h	3 h
"Dry to handle" at increased temperature	60 min/50 °C	30 min/80 °C	20 min/100 °C

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Finish Glossy.

Colours RAL, NCS, SSG, BS, MONICOLOR NOVA and SYMPHONY colour cards.

TEMASPEED tinting.

TEMALUX 70

Cleaning of equipment

APPLICATION DETAILS

Surface preparation Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)

<u>Steel surfaces:</u> Blast clean to grade Sa2½. (ISO 8501-1) If blast cleaning is not possible, phosphating is recommended for cold rolled steel to improve adhesion.

<u>Primed surfaces:</u> Oil, grease, salt and dirt are removed from the surface by appropriate means. Repair any damage to the primer coat. Note the overcoating time of primer.

(ISO 12944-4)

Primer TEMALUX 70, TEMALUX PRIMER, TEMAPRIME EE and FONTECRYL 10.

Finish TEMALUX 70 and TEMALUX 90.

Application conditions All surfaces must be dry. The temperature of the ambient air, steel surface and the

paint should not fall below +10 °C / 50 °F during application or drying. Relative humidity should not exceed 80 %. The surface temperature of the steel should remain at least

3 °C / 38 °F above the dew point.

Mixing components First stir base and hardener separately. The correct proportions of base and hardener

must be mixed thoroughly before use. Use a mechanical agitator for mixing or two

component spray equipment

Application By airless or conventional spray, brush. At spray application a "wet-in wet" technique is

recommended: first a misty coat or a thin coat, then let the solvents evaporate for

2 - 20 minutes before the final coat is applied.

In order to reach an even, smooth finish at spray application the viscosity of the paint should be correct or the nozzle pressure high enough. Depending on the temperatures of the components (base, hardener, thinner) the paint should be thinned 10 - 20 % at airless spray application, the viscosity should be 40 s DIN4 or less when the nozzle pressure is 120 - 160 bar. If a higher pressure, 160 - 260 bar, is used, thin the paint 0 - 10 %. Airless spray nozzle tip 0.011" - 0.013", spray angle shall be chosen

according to the shape of the object.

At conventional spray application the viscosity should be 20 - 25 s DIN4.

At brush application the paint should be thinned according to the circumstancies. By using air assisted electrostatic painting equipment you can improve the finish

quality, especially when using nozzle pressure below 120 bar.

When oven drying is practised, in the temperature range + 50 - 120 °C, the

evaporation time should be for 5 - 30 minutes before ovening, depending on wet film thickness and actual temperature. The advantages with oven drying are faster drying and a more even finish, especially when low nozzle pressures, 60 - 120 bar, are used.

Thinner Thinner 1048 or 1280. The suitable thinner depends on the painting conditions.

VOC The Volatile Organic Compounds amount to 300 ± 20 g/litre of paint.

HEALTH AND SAFETY Containers are provided with safety labels, which should be observed. Further

information about hazardous influences and protection are detailed in individual health

and safety data sheets.

Thinner 1048 or 1280.

A health and safety data sheet is available on request from Tikkurila Coatings Oy.

For professional use only.

tmk020802/519-s, 008 7670